CHEMICAL RESISTANCE OF BELZONA® 1111

FN 10132

	Chemical name (Synonym)	Chemical formula (CAS number)	Concentration	20 ˚C 68 ˚F	Other
Inorganic Acids	Carbonic acid	H_2CO_3 (463-79-6)	-	Ex	-
	Fluorosilicic acid	H_2SiF_6 (16961-83-4)	-	M	-
	Hydrobromic acid	HBr (10035-10-6)	10%	Ex	-
	Hydrochloric acid	HCl (7647-01-0)	35% 20% 10%	M G Ex	- - -
	Nitric acid	HNO_3 (7697-37-2)	50% 20% 10%	P G G	- - -
	Nitrous acid	HNO_2 (7782-77-6)	20%	Ex	-
	Oleum		-	P	-
	Phosphoric acid (orthophosphoric acid)	H_3PO_4 (7664-38-2)	20% 10% 5%	G G Ex	- - -
	Sulfuric acid	H_2SO_4 (7664-93-9)	98% 50% 20% 10%	P M G Ex	- - - -
Organic Acids	Acetic acid (ethanoic acid)	CH_3COOH (64-19-7)	50% 20% 10%	P M M	- - -
	Chloroacetic acid	$ClCH_2COOH$ (79-11-8)	-	M	-
	Chlorosulfonic acid (sulfurochloridic acid)	HSO_3Cl (7790-94-5)	-	M	-
	Citric acid	$C_6H_8O_7$ (77-92-9)	-	G	-
	Cresylic acid (cresol)	C_7H_8O (1319-77-3)	-	P	-
	Formic acid (methanoic acid)	HCOOH (64-18-6)	20% 10%	M M	- -
	Lactic acid (2-hydroxypropanoic acid)	$CH_3CH(OH)(COOH)$ (50-21-5/79-33-4/10326-41-7)	10%	G	-
	Phenol	C_6H_5OH (108-95-2)	80%	P	-
Alcohols	n-Butanol (butyl alcohol)	C_4H_9OH (71-36-3)	-	Ex	-
	Ethanol (ethyl alcohol)	CH_3CH_2OH (64-17-5)	-	G	-
	Ethylene glycol (ethan-1,2-diol, monoethylene glycol, MEG)	$(CH_2OH)_2$ (107-21-1)	-	Ex	-
	Glycerol (glycerine, propane-1,2,3-triol)	$HOCH_2CH(OH)CH_2OH$ (56-81-5)	-	Ex	-
	Higher alcohols	$C_nH_{(2n+1)}OH$ where n > 2	-	Ex	-

Excellent	**Ex**	Suitable for all reasonable applications including immersion.
Good	**G**	Suitable for applications involving immersion for short periods, splashing and contact with fumes.
Moderate	**M**	Suitable for use in environments contaminated by the chemical or in situations where accidental splashing can be removed either by cleaning or in the case of volatile solvents, by evaporation.
Poor	**P**	*Not suitable for any applications involving contact with the chemical itself or fumes evolved from it.*
Note:		Chemical resistance ratings are assigned based on the ability of a Belzona product to resist chemical attack and/or protect the underlying substrate. Belzona cannot guarantee the purity of the chemical, appearance or colour stability following contact.

© 2026 Belzona International Limited. All rights reserved.

CHEMICAL RESISTANCE OF BELZONA® 1111

FN 10132

	Chemical name (Synonym)	Chemical formula (CAS number)	Concentration	20 °C 68 °F	Other
Alcohols continued	Methanol (methyl alcohol)	CH_3OH (67-56-1)	-	G	-
	2-Methoxyethanol	$C_3H_8O_2$ (109-86-4)	-	Ex	-
	Propan-1-ol (Propyl alcohol)	$CH_3CH_2CH_2OH$ (71-23-8)	-	Ex	-
	Propylene glycol (1,2-Propanediol)	$CH_3CH(OH)CH_2OH$ (57-55-6)	-	Ex	-
	Secondary alcohols	R_1R_2CHOH	-	Ex	-
	Tertiary alcohols	$R_1R_2R_3COH$	-	Ex	-
Alkalis	Ammonia	NH_3 (7664-41-7)	30% 20% 10%	G Ex Ex	- - -
	Barium hydroxide	$Ba(OH)_2$ (17194-00-2)	-	Ex	-
	Calcium hydroxide (lime water)	$Ca(OH)_2$ (1305-62-0)	-	Ex	-
	Magnesium hydroxide (milk of magnesia)	$Mg(OH)_2$ (1309-42-8)	-	Ex	-
	Potassium hydroxide (caustic potash)	KOH (1310-58-3)	40% 20% 10%	G Ex Ex	- - -
	Sodium hydroxide (caustic soda)	NaOH (1310-73-2)	50% 40% 20% 10%	Ex Ex Ex Ex	 - - -
Amines & Amides	Aniline (Phenylamine)	$C_6H_5NH_2$ (62-53-3)	-	M	-
	Diethanolamine	$HN(CH_2CH_2OH)_2$ (111-42-2)	-	Ex	-
	Diethylamine	$CH_3CH_2NHCH_2CH_3$ (109-89-7)	-	P	-
	Dimethylformamide	$(CH_3)_2NC(O)H$ (68-12-2)	-	P	-
	Methylamine (25% in water)	CH_3NH_2 (74-89-5)	-	Ex	-
	Pyridine	C_5H_5N (110-86-1)	-	P	-
	Triethanolamine (TEA) (2,2',2"-nitrilotriethanol)	$N(CH_2CH_2OH)_3$ (102-71-6)	-	Ex	-
Beverages & Foodstuffs	Beer		-	Ex	-
	Cider		-	Ex	-
	Citrus juices		-	Ex	-
	Fermentation liquor		-	Ex	-
	Glucose		-	Ex	-
	Milk		-	G	-
	Sugar solution		-	Ex	-
	Vinegar		-	G	-
	Whisky and Wine		-	M	-

Excellent	**Ex**	Suitable for all reasonable applications including immersion.
Good	**G**	Suitable for applications involving immersion for short periods, splashing and contact with fumes.
Moderate	**M**	Suitable for use in environments contaminated by the chemical or in situations where accidental splashing can be removed either by cleaning or in the case of volatile solvents, by evaporation.
Poor	**P**	*Not suitable for any applications involving contact with the chemical itself or fumes evolved from it.*
Note:		Chemical resistance ratings are assigned based on the ability of a Belzona product to resist chemical attack and/or protect the underlying substrate. Belzona cannot guarantee the purity of the chemical, appearance or colour stability following contact.

© 2026 Belzona International Limited. All rights reserved.

	Chemical name (Synonym)	Chemical formula (CAS number)	Concentration	20 °C 68 °F	Other
Esters & Ethers	Amyl acetate	$CH_3COO(CH_2)_4CH_3$ (628-63-7)	-	Ex	-
	Butyl acetate	$C_6H_{12}O_2$ (123-86-4)	-	Ex	-
	Dibutyl adipate	$[CH_2CH_2CO_2(CH_2)_3CH_3]_2$ (105-99-7)	-	Ex	-
	Dibutyl phthalate	$C_{16}H_{22}O_4$ (84-74-2)	-	Ex	-
	Dibutyl sebacate	$C_{18}H_{34}O_4$ (109-43-3)	-	Ex	-
	Dioctyl adipate	$C_{22}H_{42}O_4$ (123-79-5)	-	Ex	-
	Dioctyl phthalate	$C_6H_4(C_8H_{17}COO)_2$ (117-81-7)	-	Ex	-
	Dioctyl sebacate	$(CH_2)_8(COOC_8H_{17})_2$	-	Ex	-
	Diethyl ether	$(C_2H_5)_2O$ (60-29-7)	-	Ex	-
	Diphenyl isodecyl phosphate	$C_{22}H_{31}O_4P$ (29761-21-5)	-	Ex	-
	Ethyl acetate	$CH_3COOCH_2CH_3$ (141-78-6)	-	Ex	-
	Isopropyl ether	$C_6H_{14}O$ (108-20-3)	-	Ex	-
	Methyl acetate	CH_3COOCH_3 (79-20-9)	-	Ex	-
Gases	Carbon dioxide (dry)	CO_2 (124-38-9)	-	Ex	-
	Carbon monoxide	CO (630-08-0)	-	Ex	-
	Chlorine (dry)	Cl_2 (7782-50-5)	-	Ex	-
	Hydrogen	H_2 (1333-74-0)	-	Ex	-
	Natural Gas (Methane)	CH_4	-	Ex	-
	Nitrogen	N_2 (7727-37-9)	-	Ex	-
	Nitrous oxide (dinitrogen monoxide)	N_2O (10024-97-2)	-	Ex	-
	Ozone (dry)	O_3 (10028-15-6)	-	Ex	-
	Ozone (aqueous solution)		-	M	-
	Sulphur dioxide	SO_2 (7446-09-5)	-	Ex	-
	Sulphur trioxide (sulphuric anhydride)	SO_3 (7446-11-9)	-	Ex	-

Excellent	**Ex**	Suitable for all reasonable applications including immersion.
Good	**G**	Suitable for applications involving immersion for short periods, splashing and contact with fumes.
Moderate	**M**	Suitable for use in environments contaminated by the chemical or in situations where accidental splashing can be removed either by cleaning or in the case of volatile solvents, by evaporation.
Poor	**P**	*Not suitable for any applications involving contact with the chemical itself or fumes evolved from it.*
Note:		Chemical resistance ratings are assigned based on the ability of a Belzona product to resist chemical attack and/or protect the underlying substrate. Belzona cannot guarantee the purity of the chemical, appearance or colour stability following contact.

© 2026 Belzona International Limited. All rights reserved.

CHEMICAL RESISTANCE OF BELZONA® 1111

FN 10132

	Chemical name (Synonym)	Chemical formula (CAS number)	Concentration	20 °C 68 °F	Other
Halocarbons	Carbon tetrachloride	CCl_4 (56-23-5)	-	G	-
	Chlorobenzene	C_6H_5Cl (108-90-7)	-	G	-
	Chloroform	$CHCl_3$ (67-66-3)	-	G	-
	Dry cleaning fluids		-	G	-
	Methylene chloride (dichloromethane)	CH_2Cl_2 (75-09-2)	-	P	-
	Perchloroethylene (tetrachloroethylene)	$Cl_2C=CCl_2$ (127-18-4)	-	G	-
	1,1,1, - Trichloroethane (methyl chloroform)	CH_3CCl_3 (71-55-6)	-	G	-
Hydrocarbons	Aviation fuel (AVCAT, AVGAS, AVTAG, AVTUR)	N/A	-	Ex	-
	Benzene (benzol)	C_6H_6 (71-43-2)	-	Ex	-
	Cyclohexane	C_6H_{12} (110-82-7)	-	Ex	-
	Gasoline – Ethanol free (Petrol)		-	Ex	-
	Heptane	$CH_3CH_2CH_2CH_2CH_2CH_2CH_3$ (142-82-5)	-	Ex	-
	Hexane	$CH_3CH_2CH_2CH_2CH_2CH_3$ (110-54-3)	-	Ex	-
	Iso-octane (2,2,4-trimethylpentane)	$(CH_3)_3CCH_2CH(CH_3)_2$ (540-84-1)	-	Ex	-
	Kerosene	N/A (8008-20-6)	-	Ex	-
	Paraffin	N/A (8002-74-2)	-	Ex	-
	Pentane	$CH_3CH_2CH_2CH_2CH_3$ (109-66-0)	-	Ex	-
	Styrene	$C_6H_5CH=CH_2$ (100-42-5)	-	Ex	-
	Toluene (methylbenzene, phenylmethane, toluol)	$C_6H_5CH_3$ (108-88-3)	-	Ex	-
	White Spirit (Stoddard solvent, Mineral spirits)	(8052-41-3)	-	Ex	-
	Xylene (dimethyl benzene, xylol)	$C_6H_4(CH_3)_2$ (95-47-6/108-38-3/106-42-3/1330-20-7)	-	Ex	-
Ketones	Acetone	$(CH_3)_2CO$ (67-64-1)	-	M	-
	Methyl ethyl ketone (MEK, butanone)	$CH_3C(O)CH_2CH_3$ (78-93-3)	-	M	-
Miscellaneous	Aqueous Urea Solution (Adblue)	$CO(NH_2)_2$ (57-13-6)	32.5%	Ex	-
	Brake fluid		-	Ex	-
	Drilling mud		-	Ex	-
	Emulsion paint		-	Ex	-
	Fertilizer solutions		-	Ex	-
	Grease		-	Ex	-

Excellent	**Ex**	Suitable for all reasonable applications including immersion.
Good	**G**	Suitable for applications involving immersion for short periods, splashing and contact with fumes.
Moderate	**M**	Suitable for use in environments contaminated by the chemical or in situations where accidental splashing can be removed either by cleaning or in the case of volatile solvents, by evaporation.
Poor	**P**	*Not suitable for any applications involving contact with the chemical itself or fumes evolved from it.*
Note:		Chemical resistance ratings are assigned based on the ability of a Belzona product to resist chemical attack and/or protect the underlying substrate. Belzona cannot guarantee the purity of the chemical, appearance or colour stability following contact.

© 2026 Belzona International Limited. All rights reserved.

CHEMICAL RESISTANCE OF BELZONA® 1111

FN 10132

	Chemical name (Synonym)	Chemical formula (CAS number)	Concentration	20 ˚C 68 ˚F	Other
Miscellaneous continued	Ink (water based)		-	Ex	-
	Mercury	Hg	-	Ex	-
	Mine waters (acid)		-	Ex	-
	Oil/water mixtures		-	Ex	-
	Water, distilled		-	Ex	-
	Water, fresh		-	Ex	-
	Water, sea		-	Ex	-
Oils - Mineral	Bunker oils (fuel oils)		-	Ex	-
	Crude oil		-	Ex	-
	Cutting oils, water emulsions		-	Ex	-
	Diesel oil		-	Ex	-
	Lubricating oil		-	Ex	-
	Transformer oil		-	Ex	-
Oils - Vegetable/ Animal	Castor oil		-	Ex	-
	Coconut oil		-	Ex	-
	Cod liver oil		-	Ex	-
	Corn oil		-	Ex	-
	Linseed oil		-	Ex	-
	Olive oil		-	Ex	-
Salts	Aluminium chloride (dry)	$AlCl_3$ (7446-70-0)	-	Ex	-
	Aluminium sulphate	$Al_2(SO_4)_3$ (10043-01-3)	-	Ex	-
	Alums		-	Ex	-
	Ammonium bicarbonate	$(NH_4)HCO_3$ (1066-33-7)	-	Ex	-
	Ammonium carbonate	$(NH_4)_2CO_3$ (506-87-6)	-	Ex	-
	Ammonium chloride	NH_4Cl (12125-02-9)	-	Ex	-
	Ammonium monophosphate	$NH_4H_2PO_4$ (7722-76-1)	-	Ex	-
	Ammonium phosphate (dibasic)	$(NH_4)_2HPO_4$ (7783-28-0)	-	Ex	-
	Ammonium phosphate (tribasic)	$(NH_4)_3PO_4$ (10361-65-6)	-	Ex	-
	Ammonium nitrate	NH_4NO_3 (6484-52-2)	-	Ex	-
	Ammonium sulfate	$(NH_4)_2SO_4$ (7783-20-2)	-	Ex	-
	Antimony trichloride	$SbCl_3$ (10025-91-9)	-	Ex	-
	Barium carbonate	$BaCO_3$ (513-77-9)	-	Ex	-
	Barium chloride	$BaCl_2$ (10361-37-2)	-	Ex	-
	Barium sulfate	$BaSO_4$ (7727-43-7)	-	Ex	-
	Brines		-	Ex	-
	Calcium bisulfite	$Ca(HSO_3)_2$ (13780-03-5)	-	Ex	-
	Calcium carbonate	$CaCO_3$ (471-34-1)	-	Ex	-

Excellent	**Ex**	Suitable for all reasonable applications including immersion.
Good	**G**	Suitable for applications involving immersion for short periods, splashing and contact with fumes.
Moderate	**M**	Suitable for use in environments contaminated by the chemical or in situations where accidental splashing can be removed either by cleaning or in the case of volatile solvents, by evaporation.
Poor	**P**	*Not suitable for any applications involving contact with the chemical itself or fumes evolved from it.*
Note:		Chemical resistance ratings are assigned based on the ability of a Belzona product to resist chemical attack and/or protect the underlying substrate. Belzona cannot guarantee the purity of the chemical, appearance or colour stability following contact.

© 2026 Belzona International Limited. All rights reserved.

	Chemical name (Synonym)	Chemical formula (CAS number)	Concentration	20 ˚C 68 ˚F	Other
Salts continued	Calcium chloride		-	Ex	-
	Calcium hypochlorite	$Ca(ClO)_2$ (7778-54-3)	-	Ex	-
	Calcium sulphate	$CaSO_4$ (7778-18-9)	-	Ex	-
	Chrome alum	$KCr(SO_4)_2$ (10141-00-1)	-	Ex	-
	Copper acetate	$Cu(CH_3COO)_2$ (142-71-2)	-	Ex	-
	Copper chloride	$CuCl_2$ (7447-39-4)	-	Ex	-
	Copper nitrate	$Cu(NO_3)_2$ (3251-23-8)	-	Ex	-
	Copper sulphate	$CuSO_4$ (7758-98-7)	-	Ex	-
	Ferric chloride (dry)	$FeCl_3$ (7705-08-0)	-	Ex	-
	Ferric nitrate	$Fe(NO_3)_3$ (10421-48-4)	-	Ex	-
	Ferric sulfate	$Fe_2(SO_4)_3$ (10028-22-5)	-	Ex	-
	Ferrous chloride	$FeCl_2$ (7758-94-3)	-	Ex	-
	Ferrous sulfate	$FeSO_4$ (7720-78-7)	-	Ex	-
	Lead acetate	$Pb(CH_3COO)_2$ (301-04-2)	-	Ex	-
	Magnesium bisulfate	$Mg(HSO_4)_2$ (10028-26-9)	-	Ex	-
	Magnesium chloride	$MgCl_2$ (7786-30-3)	-	Ex	-
	Magnesium sulphate (Epsom salt)	$MgSO_4$ (7487-88-9)	-	Ex	-
	Mercuric chloride	$HgCl_2$ (7487-94-7)	-	Ex	-
	Mercuric cyanide	$Hg(CN)_2$ (592-04-1)	-	Ex	-
	Nickel ammonium sulfate	$(NH_4)_2Ni(SO_4)_2$ (7785-20-8)	-	Ex	-
	Nickel chloride	$NiCl_2$ (7718-54-9)	-	Ex	-
	Nickel nitrate	$Ni(NO_3)_2$ (13138-45-9)	-	Ex	-
	Nickel sulfate	$NiSO_4$ (7786-81-4)	-	Ex	-
	Potassium aluminium sulphate (potash alum)	$KAl(SO_4)_2$ (10043-67-1)	-	Ex	-
	Potassium bisulfite	$KHSO_3$ (7773-03-7)	-	Ex	-
	Potassium bromide	KBr (7758-02-3)	-	Ex	-
	Potassium carbonate	K_2CO_3 (584-08-7)	-	Ex	-

Excellent	**Ex**	Suitable for all reasonable applications including immersion.
Good	**G**	Suitable for applications involving immersion for short periods, splashing and contact with fumes.
Moderate	**M**	Suitable for use in environments contaminated by the chemical or in situations where accidental splashing can be removed either by cleaning or in the case of volatile solvents, by evaporation.
Poor	**P**	*Not suitable for any applications involving contact with the chemical itself or fumes evolved from it.*
Note:		Chemical resistance ratings are assigned based on the ability of a Belzona product to resist chemical attack and/or protect the underlying substrate. Belzona cannot guarantee the purity of the chemical, appearance or colour stability following contact.

© 2026 Belzona International Limited. All rights reserved.

	Chemical name (Synonym)	Chemical formula (CAS number)	Concentration	20 °C 68 °F	Other
Salts continued	Potassium chlorate	$KClO_3$ (3811-04-9)	-	Ex	-
	Potassium chloride	KCl (7447-40-7)	-	Ex	-
	Potassium cyanide	KCN (151-50-8)	-	Ex	-
	Potassium dichromate	$K_2Cr_2O_7$ (7778-50-9)	-	Ex	-
	Potassium diphosphate	K_2HPO_4 (7758-11-4)	-	Ex	-
	Potassium ferricyanide	$K_3[Fe(CN)_6]$ (13746-66-2)	-	Ex	-
	Potassium ferrocyanide	$K_4[Fe(CN)_6]$ (13943-58-3)	-	Ex	-
	Potassium iodide	KI (7681-11-0)	-	Ex	-
	Potassium nitrate	KNO_3 (7757-79-1)	-	Ex	-
	Potassium permanganate	$KMnO_4$ (7722-64-7)	-	Ex	-
	Potassium sulfate	K_2SO_4 (7778-80-5)	-	Ex	-
	Potassium sulfide	K_2S (1312-73-8)	-	Ex	-
	Potassium sulphite	K_2SO_3 (10117-38-1)	-	Ex	-
	Silver nitrate	$AgNO_3$ (7761-88-8)	-	Ex	-
	Sodium acetate	CH_3COONa (127-09-3)	-	Ex	-
	Sodium aluminate	$NaAlO_2$ (1302-42-7)	-	Ex	-
	Sodium bicarbonate	$NaHCO_3$ (144-55-8)	-	Ex	-
	Sodium bisulfate	$NaHSO_4$ (7681-38-1)	-	Ex	-
	Sodium bisulfite	$NaHSO_3$ (7631-90-5)	-	Ex	-
	Sodium borate (borax)	$Na_2B_4O_7$ (1303-96-4)	-	Ex	-
	Sodium bromide	NaBr (7647-15-6)	-	Ex	-
	Sodium carbonate (soda ash)	Na_2CO_3 (497-19-8)	-	Ex	-
	Sodium chlorate	$NaClO_3$ (7775-09-9)	-	Ex	-
	Sodium chloride	NaCl (7647-14-5)	-	Ex	-
	Sodium chromate	Na_2CrO_4 (7775-11-3)	-	Ex	-
	Sodium cyanide	NaCN (143-33-9)	-	Ex	-
	Sodium fluoride	NaF (7681-49-4)	-	Ex	-

Excellent	**Ex**	Suitable for all reasonable applications including immersion.
Good	**G**	Suitable for applications involving immersion for short periods, splashing and contact with fumes.
Moderate	**M**	Suitable for use in environments contaminated by the chemical or in situations where accidental splashing can be removed either by cleaning or in the case of volatile solvents, by evaporation.
Poor	**P**	*Not suitable for any applications involving contact with the chemical itself or fumes evolved from it.*
Note:		Chemical resistance ratings are assigned based on the ability of a Belzona product to resist chemical attack and/or protect the underlying substrate. Belzona cannot guarantee the purity of the chemical, appearance or colour stability following contact.

© 2026 Belzona International Limited. All rights reserved.

CHEMICAL RESISTANCE OF BELZONA® 1111

FN 10132

	Chemical name (Synonym)	Chemical formula (CAS number)	Concentration	20 ˚C 68 ˚F	Other
Salts continued	Sodium hypochlorite (bleach)	NaClO (7681-52-9)	12%	G	-
	Sodium metaphosphate	$(NaPO_3)_6$ (10124-56-8)	-	Ex	-
	Sodium metasilicate (sodium silicate)	Na_2SiO_3 (6834-92-0)	-	Ex	-
	Sodium nitrate	$NaNO_3$ (7631-99-4)	-	Ex	-
	Sodium phosphate (dibasic)	Na_2HPO_4 (7558-79-4)	-	Ex	-
	Sodium phosphate (tribasic)	Na_3PO_4 (7601-54-9)	-	Ex	-
	Sodium sulfate	Na_2SO_4 (7757-82-6)	-	Ex	-
	Sodium sulfide	Na_2S (1313-82-2)	-	Ex	-
	Stannous chloride (tin chloride)	$SnCl_2$ (7772-99-8)	-	Ex	-
	Zinc chloride	$ZnCl_2$ (7646-85-7)	-	Ex	-
	Zinc hydrosulfite	ZnS_2O_4 (7779-86-4)	-	Ex	-
	Zinc sulfate	$ZnSO_4$ (7733-02-0)	-	Ex	-

Excellent	**Ex**	Suitable for all reasonable applications including immersion.
Good	**G**	Suitable for applications involving immersion for short periods, splashing and contact with fumes.
Moderate	**M**	Suitable for use in environments contaminated by the chemical or in situations where accidental splashing can be removed either by cleaning or in the case of volatile solvents, by evaporation.
Poor	**P**	*Not suitable for any applications involving contact with the chemical itself or fumes evolved from it.*
Note:		Chemical resistance ratings are assigned based on the ability of a Belzona product to resist chemical attack and/or protect the underlying substrate. Belzona cannot guarantee the purity of the chemical, appearance or colour stability following contact.

The technical data contained herein is based on the results of long term tests carried out in our laboratories and to the best of our knowledge is true and accurate on the date of publication. It is however, subject to change without prior notice and the user should contact Belzona to verify the technical data is correct before specifying or ordering. No guarantee of accuracy is given or implied. We assume no responsibility for rates of coverage, performance or injury resulting from use. Liability, if any, is limited to the replacement of products. No other warranty or guarantee of any kind is made by Belzona, express or implied, whether statutory, by operation of law or otherwise, including merchantability or fitness for a particular purpose. Nothing in the foregoing statement shall exclude or limit any liability of Belzona to the extent such liability cannot by law be excluded or limited.

© 2026 Belzona International Limited. All rights reserved.