CHEMICAL RESISTANCE OF BELZONA® 1391T

FN10034

	Chemical name (Synonym)	Chemical formula (CAS number)	Concentration	Chemical Resistance 20 ˚C 68 ˚F	60 ˚C 140 ˚F	90 ˚C 194 ˚F	Other
Inorganic Acids	Carbonic acid	H_2CO_3 (463-79-6)	-	Ex*	Ex	Ex	-
	Hydrochloric acid	HCl (7647-01-0)	20%	M*	P	P	-
			10%	G*	M	P	-
			5%	Ex*	G	G	-
			3%	Ex*	Ex	**Ex**	-
	Nitric acid	HNO_3 (7697-37-2)	10%	G*	M	P	-
	Nitrous acid	HNO_2 (7782-77-6)	10%	G*	M	P	-
	Phosphoric acid (orthophosphoric acid)	H_3PO_4 (7664-38-2)	10%	G*	M	P	-
			5%	Ex*	G	M	-
	Sulphuric acid	H_2SO_4 (7664-93-9)	20%	M*	M	P	-
			10%	G*	G	M	-
			5%	Ex*	Ex	G	-
			3%	Ex*	Ex	**Ex**	-
Organic Acids	Acetic acid (ethanoic acid)	CH_3COOH (64-19-7)	10%	M*	P	P	-
			5%	M*	M	P	-
			1%	G*	G	**G**	-
			0.1%	Ex*	Ex	**Ex**	-
	Phenol (hydroxybenzene)	C_6H_5OH (108-95-2)	80%	M*	P	P	-

Excellent **Ex**	no significant deterioration / barrier properties retained for greater than 52 weeks *suitable for all applications including long term immersion*
Good **G**	no significant deterioration / barrier properties retained for 12 - 52 weeks *suitable for short-term immersion and general chemical contact*
Moderate **M**	no significant deterioration / barrier properties retained for 1 - 12 weeks *suitable for applications involving short term chemical contact e.g. spillage, splashing or secondary containment*
Poor **P**	significant deterioration / loss of barrier properties after 1 week or less *not suitable for any application*
*	Product must be post cured to deliver quoted chemical resistance. As for general guidance, the coating should be subjected to the following conditions as a minimum; 1hr at 100 °C/2hrs at 90 °C/4hrs at 80 °C/8hrs at 70 °C/16hrs at 60 °C. For specific recommendations, please contact Belzona.
Ex	**Bold** text highlights real life data obtained via chemical resistance testing
Ex	Normal font indicates that the resistance has been predicted based upon partial test data and/or similar reagents
Note:	Chemical resistance ratings are assigned based on the ability of a Belzona product to resist chemical attack and/or protect the underlying substrate. Belzona cannot guarantee the purity of the chemical, appearance or colour stability following contact.

© 2026 Belzona International Limited. All rights reserved.

CHEMICAL RESISTANCE OF BELZONA® 1391T

FN10034

	Chemical name (Synonym)	Chemical formula (CAS number)	Concentration	Chemical Resistance 20 ˚C 68 ˚F	60 ˚C 140 ˚F	90 ˚C 194 ˚F	Other
Alcohols, Aldehydes and Ketones	Acetone (propanone)	$(CH_3)_2CO$ (67-64-1)	-	Ex*	-	-	55˚C 131˚F G*
	Amyl alcohol	$C_5H_{11}OH$ (71-41-0)	-	Ex*	Ex	Ex	-
	n-Butanol (butyl alcohol)	C_4H_9OH (71-36-3)	-	Ex*	Ex	Ex	-
	Ethanol (ethyl alcohol)	CH_3CH_2OH (64-17-5)	-	Ex*	Ex	-	-
	Ethylene glycol (ethan-1,2-diol, monoethylene glycol, MEG)	$(CH_2OH)_2$ (107-21-1)	-	Ex*	Ex	**Ex**	-
	Glycerol (glycerine, propane-1,2,3-triol)	$HOCH_2CH(OH)CH_2OH$ (56-81-5)	-	Ex*	Ex	Ex	-
	n-Hexanol (hexyl alcohol)	$C_6H_{13}OH$ (111-27-3)	-	Ex*	Ex	Ex	-
	Higher alcohols	$C_nH_{(2n+1)}OH$ where n > 2	-	Ex*	Ex	Ex	-
	Isopropyl alcohol (IPA) (isopropanol, propan-2-ol)	$CH_3CH(OH)CH_3$ (67-63-0)	-	Ex*	Ex	-	-
	Isobutyl alcohol (IBA) (isobutanol, 2-methylpropan-1-ol)	$(CH_3)_2CHCH_2OH$ (78-83-1)	-	Ex*	Ex	Ex	-
	Methanol (methyl alcohol)	CH_3OH (67-56-1)	-	Ex*	Ex	-	-
	Methanol solution (aqueous)	$CH_3OH_{(aq)}$ (67-56-1)	55%	Ex*	Ex	-	**79˚C 174˚F Ex**
	Methyl ethyl ketone (MEK) (2-butanone, methyl acetone)	$CH_3C(O)CH_2CH_3$ (78-93-3)	-	Ex*	G	-	-

Excellent **Ex**	no significant deterioration / barrier properties retained for greater than 52 weeks *suitable for all applications including long term immersion*
Good **G**	no significant deterioration / barrier properties retained for 12 - 52 weeks *suitable for short-term immersion and general chemical contact*
Moderate **M**	no significant deterioration / barrier properties retained for 1 - 12 weeks *suitable for applications involving short term chemical contact e.g. spillage, splashing or secondary containment*
Poor **P**	significant deterioration / loss of barrier properties after 1 week or less *not suitable for any application*
*	Product must be post cured to deliver quoted chemical resistance. As for general guidance, the coating should be subjected to the following conditions as a minimum; 1hr at 100 °C/2hrs at 90 °C/4hrs at 80 °C/8hrs at 70 °C/16hrs at 60 °C. For specific recommendations, please contact Belzona.
Ex	**Bold** text highlights real life data obtained via chemical resistance testing
Ex	Normal font indicates that the resistance has been predicted based upon partial test data and/or similar reagents
Note:	Chemical resistance ratings are assigned based on the ability of a Belzona product to resist chemical attack and/or protect the underlying substrate. Belzona cannot guarantee the purity of the chemical, appearance or colour stability following contact.

© 2026 Belzona International Limited. All rights reserved.

CHEMICAL RESISTANCE OF BELZONA® 1391T

FN10034

	Chemical name (Synonym)	Chemical formula (CAS number)	Concentration	Chemical Resistance 20 ˚C 68 ˚F	60 ˚C 140 ˚F	90 ˚C 194 ˚F	Other
Alcohols, Aldehydes and Ketones	Propan-1-ol (Propyl alcohol)	$CH_3CH_2CH_2OH$ (71-23-8)	-	Ex*	Ex	Ex	-
	Propylene glycol (1,2-Propanediol)	$CH_3CH(OH)CH_2OH$ (57-55-6)	-	Ex*	Ex	Ex	-
	Secondary alcohols	R_1R_2CHOH	-	Ex*	Ex	Ex	-
	Tertiary alcohols	$R_1R_2R_3COH$	-	Ex*	Ex	Ex	-
	Triethylene glycol (triglycol)	$HOCH_2CH_2OCH_2CH_2OCH_2CH_2OH$ (112-27-6)	-	Ex*	Ex	Ex	-
	Tetraethylene glycol (tetraglycol)	$HOCH_2CH_2OCH_2CH_2OCH_2CH_2OCH_2CH_2OH$ (112-60-7)	-	Ex*	Ex	Ex	-
Alkalis / Bases	Barium hydroxide	$Ba(OH)_2$ (17194-00-2)	-	Ex*	Ex	Ex	-
	Calcium hydroxide (lime water)	$Ca(OH)_2$ (1305-62-0)	-	Ex*	Ex	Ex	-
	Magnesium hydroxide (milk of magnesia)	$Mg(OH)_2$ (1309-42-8)	-	Ex*	Ex	Ex	-
	Potassium hydroxide (caustic potash)	KOH (1310-58-3)	40%	Ex*	Ex	Ex	-
			20%	Ex*	Ex	Ex	-
			10%	Ex*	Ex	Ex	-
	Sodium hydroxide (caustic soda)	NaOH (1310-73-2)	50%	Ex*	Ex	Ex	-
			40%	Ex*	Ex	**Ex**	-
			20%	Ex*	Ex	Ex	-
			10%	Ex*	Ex	Ex	-

Excellent	**Ex**	no significant deterioration / barrier properties retained for greater than 52 weeks *suitable for all applications including long term immersion*
Good	**G**	no significant deterioration / barrier properties retained for 12 - 52 weeks *suitable for short-term immersion and general chemical contact*
Moderate	**M**	no significant deterioration / barrier properties retained for 1 - 12 weeks *suitable for applications involving short term chemical contact e.g. spillage, splashing or secondary containment*
Poor	**P**	significant deterioration / loss of barrier properties after 1 week or less *not suitable for any application*
*		Product must be post cured to deliver quoted chemical resistance. As for general guidance, the coating should be subjected to the following conditions as a minimum; 1hr at 100 °C/2hrs at 90 °C/4hrs at 80 °C/8hrs at 70 °C/16hrs at 60 °C. For specific recommendations, please contact Belzona.
Ex		**Bold** text highlights real life data obtained via chemical resistance testing
Ex		Normal font indicates that the resistance has been predicted based upon partial test data and/or similar reagents
Note:		Chemical resistance ratings are assigned based on the ability of a Belzona product to resist chemical attack and/or protect the underlying substrate. Belzona cannot guarantee the purity of the chemical, appearance or colour stability following contact.

© 2026 Belzona International Limited. All rights reserved.

CHEMICAL RESISTANCE OF BELZONA® 1391T

FN10034

	Chemical name (Synonym)	Chemical formula (CAS number)	Concentration	Chemical Resistance 20 ˚C 68 ˚F	60 ˚C 140 ˚F	90 ˚C 194 ˚F	Other
Amines & Amides	Diethanolamine (DEA) (2,2'-iminodiethanol)	$HN(CH_2CH_2OH)_2$ (111-42-2)	-	Ex*	Ex	Ex	-
	Diethylene glycolamine (DGA) (2-(2-aminoethoxy) ethanol)	$H_2NCH_2CH_2OCH_2CH_2OH$ (929-06-6)	-	Ex*	G	M	-
	N-Methyl diethanolamine (MDEA)	$CH_3N(CH_2CH_2OH)_2$ (105-59-9)	-	Ex*	Ex	**Ex**	-
	N-Methylethanolamine (2-methylaminoethanol)	$CH_3NHCH_2CH_2OH$ (109-83-1)	-	Ex*	Ex	Ex	-
	Monoethanolamine (MEA) (2-aminoethanol)	$H_2NCH_2CH_2OH$ (141-43-5)	-	Ex*	Ex	**Ex**	-
	Sulfinol solution (50% diisopropanolamine, 25% tetramethylene sulphone, 25% water)	N/A	-	Ex*	Ex	**Ex**	-
	Triethanolamine (TEA) (2,2',2"-nitrilotriethanol)	$N(CH_2CH_2OH)_3$ (102-71-6)	-	Ex*	Ex	Ex	-
Esters and Ethers	Butyl acetate (butyl ethanoate)	$CH_3C(O)OCH_2CH_2CH_2CH_3$ (123-86-4)	-	Ex*	Ex	Ex	-
	Dibutyl phthalate (DBP) (phthalic acid dibutyl ester)	$C_6H_4(C(O)OCH_2CH_2CH_2CH_3)_2$ (84-74-2)	-	Ex*	Ex	Ex	-
	Diethyl ether (ether, ethoxyethane)	$CH_3CH_2OCH_2CH_3$ (60-29-7)	-	Ex*	-	-	-
	Dioctyl phthalate (DOP) (bis(2-ethylhexyl) phthalate, DEHP)	$C_6H_4(C(O)OCH_2CH(CH_2CH_3)CH_2CH_2CH_2CH_3)_2$ (117-81-7)	-	Ex*	Ex	Ex	-
	Ethyl acetate (ethyl ethanoate, acetic ester)	$CH_3C(O)OCH_2CH_3$ (141-78-6)	-	Ex*	Ex	-	-

Excellent	**Ex**	no significant deterioration / barrier properties retained for greater than 52 weeks *suitable for all applications including long term immersion*
Good	**G**	no significant deterioration / barrier properties retained for 12 - 52 weeks *suitable for short-term immersion and general chemical contact*
Moderate	**M**	no significant deterioration / barrier properties retained for 1 - 12 weeks *suitable for applications involving short term chemical contact e.g. spillage, splashing or secondary containment*
Poor	**P**	significant deterioration / loss of barrier properties after 1 week or less *not suitable for any application*
*		Product must be post cured to deliver quoted chemical resistance. As for general guidance, the coating should be subjected to the following conditions as a minimum; 1hr at 100 °C/2hrs at 90 °C/4hrs at 80 °C/8hrs at 70 °C/16hrs at 60 °C. For specific recommendations, please contact Belzona.
Ex		**Bold** text highlights real life data obtained via chemical resistance testing
Ex		Normal font indicates that the resistance has been predicted based upon partial test data and/or similar reagents
Note:		Chemical resistance ratings are assigned based on the ability of a Belzona product to resist chemical attack and/or protect the underlying substrate. Belzona cannot guarantee the purity of the chemical, appearance or colour stability following contact.

© 2026 Belzona International Limited. All rights reserved.

CHEMICAL RESISTANCE OF BELZONA® 1391T

FN10034

	Chemical name (Synonym)	Chemical formula (CAS number)	Concentration	Chemical Resistance 20 ˚C 68 ˚F	60 ˚C 140 ˚F	90 ˚C 194 ˚F	Other
Gases	Butane	$CH_3CH_2CH_2CH_3$ (106-97-8)	-	Ex	Ex	Ex	-
	Carbon dioxide	CO_2 (124-38-9)	-	Ex	Ex	Ex	-
	Carbon monoxide	CO (630-08-0)	-	Ex	Ex	Ex	-
	Chlorine (dry)	Cl_2 (7782-50-5)	-	Ex	Ex	Ex	-
	Ethane	C_2H_6 (74-84-0)	-	Ex	Ex	Ex	-
	Hydrogen	H_2 (1333-74-0)	-	Ex	Ex	Ex	-
	Hydrogen sulphide	H_2S (7783-06-4)	-	Ex	Ex	Ex	-
	Methane (natural gas)	CH_4 (74-82-8)	-	Ex	Ex	Ex	-
	Nitrogen	N_2 (7727-37-9)	-	Ex	Ex	Ex	-
	Nitrous oxide (dinitrogen monoxide)	N_2O (10024-97-2)	-	Ex	Ex	Ex	-
	Ozone (dry)	O_3 (10028-15-6)	-	Ex	Ex	Ex	-
	Ozone (wet)	O_3 (10028-15-6)	-	G*	M	M	-

Excellent **Ex**	no significant deterioration / barrier properties retained for greater than 52 weeks *suitable for all applications including long term immersion*
Good **G**	no significant deterioration / barrier properties retained for 12 - 52 weeks *suitable for short-term immersion and general chemical contact*
Moderate **M**	no significant deterioration / barrier properties retained for 1 - 12 weeks *suitable for applications involving short term chemical contact e.g. spillage, splashing or secondary containment*
Poor **P**	significant deterioration / loss of barrier properties after 1 week or less *not suitable for any application*
*	Product must be post cured to deliver quoted chemical resistance. As for general guidance, the coating should be subjected to the following conditions as a minimum; 1hr at 100 °C/2hrs at 90 °C/4hrs at 80 °C/8hrs at 70 °C/16hrs at 60 °C. For specific recommendations, please contact Belzona.
Ex	**Bold** text highlights real life data obtained via chemical resistance testing
Ex	Normal font indicates that the resistance has been predicted based upon partial test data and/or similar reagents
Note:	Chemical resistance ratings are assigned based on the ability of a Belzona product to resist chemical attack and/or protect the underlying substrate. Belzona cannot guarantee the purity of the chemical, appearance or colour stability following contact.

© 2026 Belzona International Limited. All rights reserved.

CHEMICAL RESISTANCE OF BELZONA® 1391T

FN10034

	Chemical name (Synonym)	Chemical formula (CAS number)	Concentration	Chemical Resistance 20 ˚C 68 ˚F	60 ˚C 140 ˚F	90 ˚C 194 ˚F	Other
Gases	Sulphur dioxide	SO_2 (7446-09-5)	-	Ex	Ex	Ex	-
	Sulphur trioxide (sulphuric anhydride)	SO_3 (7446-11-9)	-	Ex	Ex	Ex	-
Halocarbons	Chlorobenzene (benzene chloride, phenyl chloride)	C_6H_5Cl (108-90-7)	-	Ex*	G	M	-
	Chloroform (trichloromethane)	$HCCl_3$ (67-66-3)	-	Ex*	-	-	-
	Dichloromethane (DCM) (methylene chloride)	CH_2Cl_2 (75-09-2)	-	Ex*	-	-	-
Hydrocarbons	Aviation fuel (AVCAT, AVGAS, AVTAG, AVTUR)	N/A	-	Ex*	Ex	Ex	-
	Benzene (benzol)	C_6H_6 (71-43-2)	-	Ex*	Ex	-	-
	Cyclohexane	C_6H_{12} (110-82-7)	-	Ex*	Ex	-	-
	Gasoline (without Ethanol) (petrol)	N/A (8032-32-4)	-	Ex*	Ex	Ex	-
	Heptane	$CH_3CH_2CH_2CH_2CH_2CH_2CH_3$ (142-82-5)	-	Ex*	Ex	Ex	-
	Hexane	$CH_3CH_2CH_2CH_2CH_2CH_3$ (110-54-3)	-	Ex*	Ex	-	-
	Iso-octane (2,2,4-trimethylpentane)	$(CH_3)_3CCH_2CH(CH_3)_2$ (540-84-1)	-	Ex*	Ex	Ex	-
	Kerosene	N/A (8008-20-6)	-	Ex*	Ex	Ex	-

Excellent **Ex**	no significant deterioration / barrier properties retained for greater than 52 weeks *suitable for all applications including long term immersion*
Good **G**	no significant deterioration / barrier properties retained for 12 - 52 weeks *suitable for short-term immersion and general chemical contact*
Moderate **M**	no significant deterioration / barrier properties retained for 1 - 12 weeks *suitable for applications involving short term chemical contact e.g. spillage, splashing or secondary containment*
Poor **P**	significant deterioration / loss of barrier properties after 1 week or less *not suitable for any application*
*	Product must be post cured to deliver quoted chemical resistance. As for general guidance, the coating should be subjected to the following conditions as a minimum; 1hr at 100 °C/2hrs at 90 °C/4hrs at 80 °C/8hrs at 70 °C/16hrs at 60 °C. For specific recommendations, please contact Belzona.
Ex	**Bold** text highlights real life data obtained via chemical resistance testing
Ex	Normal font indicates that the resistance has been predicted based upon partial test data and/or similar reagents
Note:	Chemical resistance ratings are assigned based on the ability of a Belzona product to resist chemical attack and/or protect the underlying substrate. Belzona cannot guarantee the purity of the chemical, appearance or colour stability following contact.

© 2026 Belzona International Limited. All rights reserved.

CHEMICAL RESISTANCE OF BELZONA® 1391T

FN10034

	Chemical name (Synonym)	Chemical formula (CAS number)	Concentration	Chemical Resistance 20 ˚C 68 ˚F	60 ˚C 140 ˚F	90 ˚C 194 ˚F	Other
Hydrocarbons	Mesitylene (1,3,5-Trimethylbenzene)	$C_6H_3(CH_3)_3$ (108-67-8)	-	Ex*	Ex	Ex	-
	Mineral spirits / White spirits (Stoddard solvent)	N/A (8052-41-3)	-	Ex*	Ex	Ex	-
	Naphtha	N/A (8030-30-6)	-	Ex*	Ex	Ex	-
	Naphthalene (naphthalin, white tar)	$C_{10}H_8$ (91-20-3)	-	Ex*	Ex	Ex	-
	Paraffin	N/A (8002-74-2)	-	Ex*	Ex	Ex	-
	Pentane	$CH_3CH_2CH_2CH_2CH_3$ (109-66-0)	-	Ex*	-	-	-
	Toluene (methylbenzene, phenylmethane, toluol)	$C_6H_5CH_3$ (108-88-3)	-	Ex*	Ex	**Ex**	-
	Xylene (dimethyl benzene, xylol)	$C_6H_4(CH_3)_2$ (95-47-6/108-38-3/106-42-3/1330-20-7)	-	Ex*	Ex	Ex	-
Miscellaneous	Aqueous Urea Solution (Adblue)	$CO(NH_2)_2$ (57-13-6)	32.5%	**Ex**	-	-	-
	Nalco DVE4D002 Corrosion Inhibitor	N/A	-	Ex*	G	-	-
	Nalco DVE4D006 Corrosion Inhibitor	N/A	-	Ex*	G	-	-
	Nalco EC1317A Corrosion inhibitor	N/A	-	Ex*	Ex	-	-
	Nalco EC6303A Oxygen Scavenger	N/A	-	Ex*	Ex	-	-

Excellent **Ex**	no significant deterioration / barrier properties retained for greater than 52 weeks *suitable for all applications including long term immersion*
Good **G**	no significant deterioration / barrier properties retained for 12 - 52 weeks *suitable for short-term immersion and general chemical contact*
Moderate **M**	no significant deterioration / barrier properties retained for 1 - 12 weeks *suitable for applications involving short term chemical contact e.g. spillage, splashing or secondary containment*
Poor **P**	significant deterioration / loss of barrier properties after 1 week or less *not suitable for any application*
*	Product must be post cured to deliver quoted chemical resistance. As for general guidance, the coating should be subjected to the following conditions as a minimum; 1hr at 100 °C/2hrs at 90 °C/4hrs at 80 °C/8hrs at 70 °C/16hrs at 60 °C. For specific recommendations, please contact Belzona.
Ex	**Bold** text highlights real life data obtained via chemical resistance testing
Ex	Normal font indicates that the resistance has been predicted based upon partial test data and/or similar reagents
Note:	Chemical resistance ratings are assigned based on the ability of a Belzona product to resist chemical attack and/or protect the underlying substrate. Belzona cannot guarantee the purity of the chemical, appearance or colour stability following contact.

© 2026 Belzona International Limited. All rights reserved.

CHEMICAL RESISTANCE OF BELZONA® 1391T

FN10034

	Chemical name (Synonym)	Chemical formula (CAS number)	Concentration	Chemical Resistance 20 ˚C 68 ˚F	60 ˚C 140 ˚F	90 ˚C 194 ˚F	Other
Miscellaneous	Nalco EC6481A Hydrate Inhibitor	N/A	-	Ex*	Ex	-	-
	Nalco EC6622A Low Dosage Hydrate Inhibitor (LDHI)	N/A	-	Ex*	Ex	-	-
	Nalco EC9356A Hydrogen Sulphide Scavenger	N/A	-	Ex*	Ex	-	-
	Nalco O3VD123 Corrosion Inhibitor	N/A	-	Ex*	G	-	-
	Nalco Ultimer 7751 Flocculant Water Treatment	N/A	-	Ex*	Ex	-	-
	Sour oil / Brine mix	N/A	-	Ex*	Ex	Ex	120˚C 248˚F Ex
	Water	H_2O (7732-18-5)	-	Ex*	Ex	Ex	**130˚C 266˚F Ex**

Excellent	**Ex**	no significant deterioration / barrier properties retained for greater than 52 weeks *suitable for all applications including long term immersion*
Good	**G**	no significant deterioration / barrier properties retained for 12 - 52 weeks *suitable for short-term immersion and general chemical contact*
Moderate	**M**	no significant deterioration / barrier properties retained for 1 - 12 weeks *suitable for applications involving short term chemical contact e.g. spillage, splashing or secondary containment*
Poor	**P**	significant deterioration / loss of barrier properties after 1 week or less *not suitable for any application*
*		Product must be post cured to deliver quoted chemical resistance. As for general guidance, the coating should be subjected to the following conditions as a minimum; 1hr at 100 °C/2hrs at 90 °C/4hrs at 80 °C/8hrs at 70 °C/16hrs at 60 °C. For specific recommendations, please contact Belzona.
Ex		**Bold** text highlights real life data obtained via chemical resistance testing
Ex		Normal font indicates that the resistance has been predicted based upon partial test data and/or similar reagents
Note:		Chemical resistance ratings are assigned based on the ability of a Belzona product to resist chemical attack and/or protect the underlying substrate. Belzona cannot guarantee the purity of the chemical, appearance or colour stability following contact.

The technical data contained herein is based on the results of long term tests carried out in our laboratories and to the best of our knowledge is true and accurate on the date of publication. It is however, subject to change without prior notice and the user should contact Belzona to verify the technical data is correct before specifying or ordering. No guarantee of accuracy is given or implied. We assume no responsibility for rates of coverage, performance or injury resulting from use. Liability, if any, is limited to the replacement of products. No other warranty or guarantee of any kind is made by Belzona, express or implied, whether statutory, by operation of law or otherwise, including merchantability or fitness for a particular purpose. Nothing in the foregoing statement shall exclude or limit any liability of Belzona to the extent such liability cannot by law be excluded or limited.

© 2026 Belzona International Limited. All rights reserved.