

Belzona 2211

FN10143 (MP HI-BUILD ELASTOMER)



INSTRUCTIONS FOR USE

1. TO ENSURE AN EFFECTIVE MOLECULAR WELD

a) SURFACE PREPARATION

(i) Metallic Surfaces

Remove all loose surface contamination and degrease with **Belzona® 9111** (Cleaner/Degreaser) or any other effective cleaner which does not leave a residue, e.g. methyl ethyl ketone (MEK).

Grit blast to a minimum 3 mil (75 microns) profile. Where blasting is not practical, thorough mechanical grinding may be considered, except for applications involving tensile loads, such as expansion joints, and all applications involving immersion and/or fluid flow.

(ii) Flexible Surfaces (e.g. rubbers)

NOTE: Belzona® 9111 can draw processing oils and waxes to the surface of some rubbers, particularly when new, which then impairs adhesion of **Belzona® 2211**. Test for this on a small area. If, on rubbing with a rag moistened with **Belzona® 9111**, a greasy film appears, the surface should not be degreased, but simply abraded. Undercut fine edges with a sharp knife and scuff the surface with a rotary wire brush or suitable roughing tool.

Brush away loose contamination and degrease again.

(iii) Concrete Surfaces

Remove all paint, tar and any other coatings.

Any surface to which **Belzona® 2211** is to be applied must be clean, firm and dry. Wash old concrete down with detergent to remove oil, grease and dust. Use clean water to wash away the detergent.

Allow new concrete to cure for a minimum of 28 days or until the moisture content is below 6% using a Protimeter.

Blast clean, or mechanically scarify the surface to remove all loose material and surface laitance.

(iv) GRP & Existing Belzona Surfaces

When using **Belzona® 2211** to coat GRP surfaces, the surface must be abraded using mechanical sanding equipment, followed by conditioning as below.

When using **Belzona® 2211** to overcoat a surface which has been treated with a **Belzona® 1000** Series product (except **Belzona® 1221** (Super E-Metal), the **Belzona® 1000** Series product must first be allowed to fully cure, the surface prepared as outlined in section 1 (a) (i), and **Belzona® 2911**, **Belzona® 2921** or **Belzona® 2941** applied as outlined in section 1 (b).

Application of **Belzona® 2211** over **Belzona® 1221** can be carried out up to 4 hours after the application of **Belzona® 1221** without the need of any surface treatment other than removal of contamination. When overcoating **Belzona® 1221** after this time, the surface should be abraded, followed by conditioning as in Section 1 (b).

b) CONDITIONING

All surfaces must be Conditioned before applying **Belzona® 2211**. Please see table below for guidance on the recommended Conditioner based on the substrate type and service conditions:

Substrate Type & Service Conditions	Possible Conditioner Choice		
	Belzona® 2911	Belzona® 2921	Belzona® 2941
Metallic surfaces in wet/immersed environments	×	×	✓
Metallic surfaces in dry environments	✓	✓	✓
Flexible surfaces e.g., Rubber in wet/immersed environments	✓	✓	×
Flexible surfaces e.g., Rubber in dry environments	✓	✓	×
Concrete surfaces in wet/immersed environments	×	×	✓
Concrete surfaces in dry environments	✓	✓	✓
GRP and other Belzona coatings in wet/immersed environments	✓	✓	✓✓
GRP and other Belzona coatings in dry environments	✓	✓	✓

× - Not suitable for use
✓ - Suitable for use
✓✓ - Best recommendation

Apply a thin, even coat of **Belzona® Conditioner** onto the surface. A brush should be used as a stipple.

Practical coverage rate:

Belzona® 2941 19.8 sq.ft. (1.83 sq.m) per unit, on metallic substrates.

Belzona® 2911 and **Belzona® 2921**, 13 sq.ft. (1.25 m²) per unit, on smooth substrates. On well roughened rubber substrates this could be reduced by as much as 50%.

The **Belzona® Conditioner** must be touch dry before overcoating with **Belzona® 2211**. This will depend on the **Belzona® Conditioner** selected, prevailing temperature, relative humidity and substrate. At 68°F (20°C) and 50% relative humidity, the touch dry state will be achieved after the times given when applied to a steel surface.

Conditioner	Touch Dry	Max. Overcoating
Belzona® 2911	45 mins	24 hours
Belzona® 2921	75 mins	
Belzona® 2941	8 hours	

NOTE:

- Relative humidity should be between 30 & 90% and surface temperature at least 5°F (3°C) above dew point during the application and drying of the Conditioner.
- At lower temperatures and humidity, a longer drying time is required.
- These times may be extended when applied to rubber substrates.
- If in doubt leave Conditioner longer to dry but under no circumstances should maximum overcoat time be exceeded.

NOTE: Belzona® 2911 has an 18 month shelf life and **Belzona® 2921 & Belzona® 2941** have a 24 month shelf life from date of manufacture when stored at 41 - 77°F (5 - 25°C) and must be used before the stated "use by" date.

WHERE BELZONA® 2211 SHOULD NOT ADHERE

Brush on a thin layer of **Belzona® 9411** (Release Agent) and allow to dry for 15 - 20 minutes before proceeding to step 2.

2. COMBINING THE REACTIVE COMPONENTS

Complete mixing is the most important step in the use of **Belzona® 2211**.

- Transfer the entire contents of the Base and Solidifier containers onto the **Belzona®** Working Surface.
- Mix together for at least 3 minutes until the material is of an even colour and consistency.

For mixing small quantities of **Belzona® 2211** the mixing ratio is:

3.0 parts Base: 1 part Solidifier by Volume, or

2.3 parts Base: 1 part Solidifier by Weight.

It is important that the mixing ratios are accurately utilized.

- Remove the plastic cover from the top of the Base container but make sure it is replaced after measuring out has been completed.
- Apply one portion of Solidifier to the **Belzona®** Working Surface followed by three equally sized portions of Base.
- Mix as in (b) above.

NOTES:

1. MIXING AT LOW TEMPERATURES

To ease mixing when the material temperature is below 41°F (5°C), warm the Base and Solidifier containers until the contents attain a temperature of 68 - 70°F (20 - 25°C).

2. WORKING LIFE

From the commencement of mixing, **Belzona® 2211** must be used within the times shown below.

Temperature	50°F (10°C)	68°F (20°C)	86°F (30°C)	104°F (40°C)
Use all material within	25 min.	15 min.	10 min.	7 min.

3. VOLUME CAPACITY OF MIXED BELZONA® 2211

28.5 cu.in. (467 cm³) per 550 g unit.

3. APPLYING THE BELZONA® 2211

FOR BEST RESULTS

Do not apply when:-

- The temperature is below 41°F (5°C) or the relative humidity is above 90%.
- Rain, snow, fog or mist is present.
- There is moisture on the surface or is likely to be deposited by subsequent condensation.
- The working environment is likely to be contaminated by oil/grease from adjacent equipment or smoke from kerosene heaters or tobacco smoking.

- Apply the **Belzona® 2211** directly onto the prepared surface with the plastic applicator or spatula provided. Press down firmly to remove entrapped air and to ensure maximum contact with the surface.
- Contour the **Belzona® 2211** to the correct profile with the plastic applicator.

CLEANING

Mixing tools should be cleaned immediately after use with **Belzona® 9111** or any other effective solvent e.g. Methyl ethyl ketone (MEK). Application tools should be cleaned using a suitable solvent such as **Belzona® 9121**, MEK, acetone or cellulose thinners.

4. COMPLETION OF THE MOLECULAR REACTION

Allow **Belzona® 2211** to solidify as below before subjecting it to the conditions indicated:

	Light loading	Full mechanical loading	Immersion in chemicals
50°F/10°C	24 hours	72 hours	5 days
68°F/20°C	12 hours	36 hours	3 days
86°F/30°C	9 hours	32 hours	2.5 days
104°F/40°C	6 hours	28 hours	2 days

These times are for a thickness of approximately 0.10 ins (0.25 cm); they will be reduced for thicker sections and extended for thinner sections.

5. STORAGE

Once opened, **Belzona® 2211** should be used as soon as possible. To maximize shelf life (up to 4 weeks at 68°F (20°C)) of partially used product, the Base container should be re-sealed using the plastic overcap provided. A surface skin may result during this period but after removal the remaining material can be used in the normal way.

Containers should be stored in a dry environment at a temperature of not more than 86°F (30°C).

6. OVERCOATING

Application of subsequent layers of **Belzona® 2211** can be carried out without need of any surface treatment other than removal of contamination in accordance with the below maximum overcoat times:

Temperature	<50% Relative humidity	>50% Relative humidity
10°C/50°F	32 hrs	24 hrs
20°C/68°F	16 hrs	12 hrs
30°C/86°F	12 hrs	9 hrs
40°C/104°F	10 hrs	6 hrs

If the maximum overcoat time is exceeded or for overcoating of aged or weathered **Belzona® 2211**, the surface preparation techniques for flexible surfaces described in Section 1 should be followed.

HEALTH & SAFETY INFORMATION

Please read and make sure you understand the relevant Safety Data Sheets.

The technical data contained herein is based on the results of long term tests carried out in our laboratories and to the best of our knowledge is true and accurate on the date of publication. It is however subject to change without prior notice and the user should contact Belzona to verify the technical data is correct before specifying or ordering. No guarantee of accuracy is given or implied. We assume no responsibility for rates of coverage, performance or injury resulting from use. Liability, if any, is limited to the replacement of products. No other warranty or guarantee of any kind is made by Belzona, express or implied, whether statutory, by operation of law or otherwise, including merchantability or fitness for a particular purpose.

Nothing in the foregoing statement shall exclude or limit any liability of Belzona to the extent such liability cannot by law be excluded or limited.

Copyright © 2023 Belzona International Limited. Belzona® is a registered trademark.

*Belzona products are
manufactured under an
ISO 9001 Registered
Quality Management System*

