

PRODUCT SPECIFICATION SHEET

BELZONA 3111

FN10221



GENERAL INFORMATION

Product Description:
A single component formulated acrylic ester copolymer emulsion. It is used in conjunction with **Belzona 3911** (PSC Surface Conditioner) or **Belzona 3921** (GSC Surface Conditioner) and **Belzona 9311** (Reinforcing Sheet).

This liquid base binds to the **Belzona 9311** to form a tough, flexible and elastic polymeric film which can tightly follow all roof contours. For preventive maintenance and repairs, the system provides long term weatherproofing and water-proofing of almost all types of roof substrate and offers outstanding protection against infrared and ultra-violet radiation, and natural and industrial pollutants. It is impermeable to liquid water, but permeable to water vapor, thus allowing a moist roof to breathe. Also used to water and weatherproof non-roof structures such as storage tank bases.

Application Areas:
When applied as detailed in the Belzona Instructions for Use (IFU), the system is ideally suited for application to the following:

- | | | |
|----------------|-------------------|---------------------------|
| - Gutters | - Parapet Walls | - Glazing Bars |
| - Joints | - Seams | - Flashings |
| - Ponded Areas | - Flat Roof Areas | - Complex Roofs and Domes |
| | | - Tank Base Sealing |

APPLICATION INFORMATION

Drying Time Applied under good drying conditions, will be water resistant within 30 minutes of application. Under cool or humid conditions, this time will be extended. The product should not be applied when the relative humidity is above 90% or the surface temperature is below 41°F (5°C).	Properties Appearance Colour Odour Density Gel strength at 77°F (25°C) Freezing point Volatile by volume	Thixotropic liquid Available in Grey and White Very slight ammoniacal 1.235 - 1.275 g/cm³ 80 - 110 g/cm 32°F (0°C) 38.0%
Coverage Rates The first layer is applied to a dry film thickness of 10 mil (250 micron). This dry film thickness measurement includes the synthetic reinforcing sheet. The second layer should be applied to a dry film thickness of 6 mil (150 micron), giving an overall film thickness of approximately 16 mil (400 micron). Refer to the IFU for a guide to practical coverage rates.		

The above application information serves as introductory guide only. For full application details including the recommended application procedure/technique, refer to the Belzona IFU which is enclosed with each packaged product.

PRODUCT SPECIFICATION SHEET

BELZONA 3111

FN10221



ELONGATION PROPERTIES

The elongation of the reinforced system after 7 days cure at 68°F (20°C) when tested against BS 2782 or similar test method is typically:

20% lengthwise,
100% crosswise.

HEAT RESISTANCE

In accordance with European Technical Assessment (ETA 05-0075) the Belzona 3111 system is categorized for use in climatic zone M (temperate) with minimum surface temperature of -20°C and maximum 80°C)

SOLAR REFLECTANCE & EMITTANCE

Solar Reflectance

When tested in accordance with ASTM E903, subjected to wavelengths of 300 nm to 2250 nm, the solar reflectance will typically range between:

0.792 – 0.790 White

Emittance

When tested in accordance with ASTM C1371, the average emissivity is typically:

0.915 White

Solar Reflectance Index

When tested in accordance with ASTM E1980, the solar reflectance index is typically:

98.95% White

TEAR STRENGTH

The Tear Strength of the reinforced system after 7 days cure at 68°F (20°C), when tested in accordance with ASTM D624, will typically be:

188 pli (33.0 N/mm) lengthwise,
188 pli (33.0 N/mm) crosswise

TENSILE PROPERTIES

Tensile Strength

The tensile strength of the reinforced system after 7 days at 68°F (20°C) when tested against BS 2782 or similar test method is typically:

1450 psi (10.0 N/mm²) lengthwise,
580 psi (4.0 N/mm²) crosswise

VAPOR RESISTANCE

The vapor resistance of the reinforced system after 7 days cure at 68°F (20°C) is typically 33 MN/sq

WATER VAPOR PERMEABILITY

When tested in accordance with ASTM E96 the fully reinforced system after 7 days cure at 68°F (20°C) will have the following typical values:

Water vapor permeability 30g/m²/24hrs
Permeance 2.16 US Perms

SHELF LIFE

Belzona 3111 shall have a shelf life of 5 years from date of manufacture when stored in original unopened containers between 41°F (5°C) and 86°F (30°C).

APPROVALS/ACCEPTANCES



PRODUCT SPECIFICATION SHEET

BELZONA 3111

FN10221



WARRANTY

This product will meet the performance claims stated herein when material is stored and used as instructed in the Belzona Information For Use leaflet. Belzona ensures that all its products are carefully manufactured to ensure the highest quality possible and are tested strictly in accordance with universally recognized standards (ASTM, ANSI, BS, DIN, ISO, etc.). Since Belzona has no control over the use of the product described herein, no warranty for any application can be given.

AVAILABILITY AND COST

Belzona 3111 is available from a network of Belzona Distributors throughout the world for prompt delivery to the application site. For information, consult the Belzona Distributor in your area.

MANUFACTURER / SUPPLIER

Belzona Limited,
Claro Road, Harrogate,
HG1 4DS, UK

Belzona Inc.
14300 NW 60th Ave,
Miami Lakes, FL, 33014, USA

HEALTH AND SAFETY

Prior to using this material, please consult the relevant Safety Data Sheets.

TECHNICAL SERVICE

Complete technical assistance is available and includes fully trained Technical Consultants, technical service personnel and fully staffed research, development and quality control laboratories.

The technical data contained herein is based on the results of long term tests carried out in our laboratories and to the best of our knowledge is true and accurate on the date of publication. It is however subject to change without prior notice and the user should contact Belzona to verify the technical data is correct before specifying or ordering. No guarantee of accuracy is given or implied. We assume no responsibility for rates of coverage, performance or injury resulting from use. Liability, if any, is limited to the replacement of products. No other warranty or guarantee of any kind is made by Belzona, express or implied, whether statutory, by operation of law or otherwise, including merchantability or fitness for a particular purpose.

Nothing in the foregoing statement shall exclude or limit any liability of Belzona to the extent such liability cannot by law be excluded or limited.

Copyright © 2024 Belzona International Limited. Belzona® is a registered trademark.

*Belzona products are
manufactured under an
ISO 9001 Registered
Quality Management System*

